



# Mirafi<sup>®</sup> FW402

Mirafi<sup>®</sup> FW402 geotextile is composed of high-tenacity monofilament polypropylene yarns, which are woven into a stable network such that the yarns retain their relative position. Mirafi<sup>®</sup> FW402 geotextile is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Wide Width Tensile Strength	ASTM D 4595	kN/m (lbs/in)	35.0 (200)	24.5 (140)
Grab Tensile Strength	ASTM D 4632	N (lbs)	1624 (365)	890 (200)
Grab Tensile Elongation	ASTM D 4632	%	24	10
Trapezoid Tear Strength	ASTM D 4533	N (lbs)	512 (115)	334 (75)
CBR Puncture Strength	ASTM D 6241	N (lbs)	3004 (675)	
Apparent Opening Size (AOS) <sup>1</sup>	ASTM D 4751	mm (U.S. Sieve)	0.43 (40)	
Percent Open Area	COE-02215	%	10	
Permittivity	ASTM D 4491	sec <sup>-1</sup>	2.1	
Permeability	ASTM D 4491	cm/sec	0.14	
Flow Rate	ASTM D 4491	l/min/m <sup>2</sup> (gal/min/ft <sup>2</sup> )	5907 (145)	
UV Resistance (at 500 hours)	ASTM D 4355	% strength retained	90	

<sup>1</sup>ASTM D 4751: AOS is a Maximum Opening Diameter Value

Physical Properties	Test Method	Unit	Typical Value
Mass/Unit Area	ASTM D 5261	g/m <sup>2</sup> (oz/yd <sup>2</sup> )	207 (6.1)
Thickness	ASTM D 5199	mm (mils)	0.7 (27)
Roll Dimensions (width x length)	--	m (ft)	3.8 (12.5) x 91 (300)
Roll Area	--	m <sup>2</sup> (yd <sup>2</sup> )	348 (417)
Estimated Roll Weight	---	kg (lbs)	76.6 (169)

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

