



**FIRE  
TECHNOLOGY  
SERVICES**

Unit 4B Stag Industrial Estate  
Atlantic Street, Broadheath  
Altrincham, Cheshire  
WA14 5DW  
United Kingdom

Tel: +44 (0)161 929 8056  
Fax: +44 (0)161 929 8070  
Web: [www.bttg.co.uk](http://www.bttg.co.uk)

---

## CONFIDENTIAL REPORT

**Ref:** 30/04843/4 Page 1 of 2

**Date:** 1 February 2010

**Client:** TenCate Outdoor Fabrics  
P.C. Stamstraat 19  
7442 ZA Nijverdal  
The Netherlands

**Job title:** Flammability testing of one woven fabric

**Client's order or ref no:** Letter 003/10

**Date of receipt:** 13 January 2010

**Description of sample(s):** One woven fabric, referenced:  
TenCate Campshield™ – FR0001 Comfort

**Work requested:** Flammability testing to BS 7837: 1996

Uncertainty: An estimation of uncertainty of measurement has not been taken into account when making a judgement to any pass/fail criteria.



This report is incomplete without all the pages specified above,  
together with a copy of our standard terms of business.  
The supply of all goods and services is subject to our standard terms of business,  
copies of which are available on request or at [www.bttg.co.uk/PDFs/Terms\\_Conditions.pdf](http://www.bttg.co.uk/PDFs/Terms_Conditions.pdf)  
Reg. Office: BTTG Testing & Certification Limited,  
Unit 14, Wheel Forge Way, Trafford Park, Manchester, M17 1EH, United Kingdom.  
Company No. 4669650 VAT No. 816 740 526  
© BTTG Testing & Certification Limited 2010



1066

**Ref:** 30/04843/4 Page 2 of 2

**Client:** TenCate Outdoor Fabrics

**Sample:** One woven fabric, referenced:  
TenCate Campshield™ – FR0001 Comfort

**Performance Standard:** BS 7837: 1996

**Test Method:** BS 5438: 1989 Test 2B (Bottom edge ignition) with filter paper  
Flame application time = 10s  
Trimmed edge  
Outer face towards burner

**Cleansing Pretreatment:** Watersoaked according to BS 5651: 1989 Clause 3

**Summary of Results:**

“These results were obtained using the specified test conditions and do not necessarily represent the behaviour of the test material under other conditions of test or use.”

Specimen	1↑	2↓	3↑	4→	5←	6→
Duration of flaming, s	0	0	0	0	0	0
Duration of afterglow, s	10	12	15	19	19	20
Flaming debris	No	No	No	No	No	No
Flame to edge	No	No	No	No	No	No
Glow to edge	No	No	No	No	No	No
Max damaged length, mm	32	32	33	42	33	32
Ignition of filter paper	No	No	No	No	No	No

**Assessment:**

BS 7837: 1996 Requirements

*The sample shall be deemed to perform satisfactorily (pass), if, for at least five of the six test specimens: (a) the duration of flaming does not exceed 5s after removal of the igniting flame; and (b) the lowest boundary of any flame does not reach the upper or either vertical edge; and (c) the filter paper does not smoulder or flame.*

This woven fabric complies with the requirements of BS 7837: 1996.

----- END OF REPORT -----

**Reported by:** ..... *P.M. Collinson* ..... P M Collinson (Laboratory Technician)

**Countersigned by:** ..... *M.T. Healey* ..... M T Healey (Principal Technician)



This report is incomplete without all the pages specified above, together with a copy of our standard terms of business.  
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request or at [www.bttg.co.uk/PDFs/Terms\\_Conditions.pdf](http://www.bttg.co.uk/PDFs/Terms_Conditions.pdf)  
Reg. Office: BTTG Testing & Certification Limited,  
Unit 14, Wheel Forge Way, Trafford Park, Manchester, M17 1EH, United Kingdom.  
Company No. 4669650 VAT No. 816 740 526  
© BTTG Testing & Certification Limited 2010

