



TENCATE
Quantum3D®
 1-Layer

FACE CLOTH: GoldCheck™ pattern, 100% NOMEX® fiber (spun/filament)
BATT: 1 layer of 3D; fiber composition NOMEX®/KEVLAR® fiber
QUILT THREAD: Diamond Quilt™ pattern, 100% Aramid
WEIGHT: 6.2 oz (sq yd)
COLOR: Gold

QUANTUM3D® takes thermal barrier technology to an entirely new level. Its patent-pending process design provides better insulation and moisture management. And, its slick face cloth provides ease of movement and greater flexibility.

- **Thermal Protection**—Combined with any Southern Mills turnout gear outer shell, and 3-layer Crosstech®, QUANTUM3D 1-layer provides the same high level of thermal insulation as a composite containing QUANTUM3D 2-layer and 2-layer Crosstech.
- **Maximum Flexibility**—The most flexible thermal barrier on the market. Thin and ultra-light (6.2 oz/yd²) with an easy on/off slick face cloth.
- **Moisture Management**—WICKWELL™ Plus technology moves perspiration away from body, spreads moisture for improved dissipation and unmatched wickability.
- **Durability & Wear Life**—Outstanding pilling resistance. Maintains three-dimensional and physical integrity after laundering and abrasion.
- **PEAK PERFORMANCE SYSTEM™**—Because of QUANTUM3D's superior performance it has been selected as the thermal barrier component for the PEAK PERFORMANCE SYSTEM.

QUANTUM3D delivers peace of mind when lives are on the line. Only by TenCate SouthernMills.

PHYSICAL PROPERTIES	QUANTUM3D® 1-Layer	NFPA 1971-2007 Edition Requirements
Trapezoidal Tear Strength (lbs) Initial (warp x fill) After 5 launderings (warp x fill)	ASTM D 5587 80 x 70 75 x 65	5.0 min
Thermal Protective Performance (cal/cm²) TPP with MILLENIA™ XT, Crosstech® Type 4A TPP w/ GEMINI™ w/ Matrix® Technology, Crosstech® Type 4A	NFPA 1971-2007 38 - 40 38 - 40	35.0 min 35.0 min
Total Heat Loss (W/m2) THL with MILLENIA™ XT, Crosstech® Type 4A THL w/ GEMINI™ w/ Matrix® Technology, Crosstech® Type 4A	NFPA 1971-2007 240-260 240-260	205 min 205 min
Heat Resistance	NFPA 1971-2007 Pass	Shall not melt, separate or ignite
Vertical Flammability Char Length in inches (warp x fill) (Initial) Char Length in inches (warp x fill) (After 5 launderings) After Flame in seconds (warp x fill)	ASTM D 6413 <1.5 <1.0 <0.5	4.0 max 2.0 max
Thermal Shrinkage (%) 500°F at 5 minutes (warp x fill) After 5 launderings (warp x fill)	NFPA 1971-2007 < 1.0 x < 1.0 < 1.0 x < 1.0	10.0 max 10.0 max
Laundry Shrinkage (%) After 5 launderings (cotton sturdy cycle) (warp x fill)	AATCC 135 < 5.0 x < 5.0	5.0 max



TENCATE™
SOUTHERNMILLS™

The Most Trusted Name In Protective Fabrics.

SOUTHERN MILLS, Inc.
 6501 Mall Blvd.
 P.O. Box 289
 Union City, GA 30291
 Phone: 770.969.1000
 Fax: 770.969.6846
 Toll Free: 800.241.8630
www.southernmills.com

To the best of our knowledge, the information contained herein is accurate. However, SOUTHERN MILLS assumes no liability whatsoever for the accuracy or completeness of the information contained herein. Users of any substance must satisfy themselves by independent investigation that the material can be used safely. We have described certain hazards, but we cannot guarantee that these are the only hazards.

©2009 SOUTHERN MILLS, Inc. TENCATE is a trademark of ROYAL TEN CATE NV. MILLENIA, GEMINI and WICKWELL are trademarks of SOUTHERN MILLS, Inc. Diamond Quilt, GoldCheck and the appearance of the QUANTUM3D face cloth are trademarks of Southern Mills, Inc. CALDURA and QUANTUM3D are registered trademarks of SOUTHERN MILLS, Inc. GEMINI is made under the MATRIX™ Technology License from PBI Performance Products, Inc. U.S. Patent No. 6,624,096 and other U.S. and foreign patents pending. MATRIX Technology is a registered trademark of PBI Performance Products, Inc. and is used with permission. Crosstech is a registered trademark of W.L. Gore & Associates. DuPont™, NOMEX® and KEVLAR® are trademarks or registered trademarks of DuPont or its affiliates. PEAK PERFORMANCE SYSTEM and its design are trademarks of SOUTHERN MILLS, Inc. SOUTHERN MILLS, Inc. patents pending.