



10309, 10319 LENO/LOCK SHADE

Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Weight	ASTM D 5261	oz/yd ²	2.0	
Grab Tensile Strength	ASTM D 4632	lbs	65	80
Trapezoid Tear Strength	ASTM D 4533	lbs	40	50
Shade		%	30	
UV Resistance (at 500 hours)	ASTM D 4355	% strength retained	90	

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2010 TenCate Geosynthetics North America
 Nicolón® is a registered trademark of Nicolón Corporation



FGS000630
 ETQR6

