



## SOLID TENNIS WINDSCREEN

21612 BLACK/GREEN  
21619 BLACK

Mechanical Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs	420	225
Trapezoid Tear Strength	ASTM D4533	lbs	125	90
Shade		%	90	
Air Flow	ASTM D737	cfm	>150	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D5261	oz/yd <sup>2</sup>	6.1
Construction		EPI/PPI	30 x 16
Fiber Content			100% PP

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2012 TenCate Geosynthetics North America  
Nicolon<sup>®</sup> is a registered trademark of Nicolon Corporation

