



## POOL SKIMMER

23105 Light Blue

23109 Black

Mechanical Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D 4632	lbs	126	109
Trapezoid Tear Strength	ASTM D 4533	lbs	62	42
Abrasion	ASTM D 4886	% strength retained	95	
Water Flow	ASTM D 4491	gpm	340	
Shade		%	34	
UV Resistance at 3000 hours	ASTM G 154	%	75	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D 5261	oz/yd <sup>2</sup>	2.3
Thickness	ASTM D 5199	mils	19
Construction		EPI/PPI	20 x 20
Fiber Content		100% Polypropylene	

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2010 TenCate Geosynthetics North America  
 Nicolon® is a registered trademark of Nicolon Corporation

