



## 27319 TRUCK COVER

Mechanical Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs	450	350
Trapezoid Tear Strength	ASTM D4533	lbs	210	175
Mullen Burst	ASTM D3786	psi	750	
Puncture Strength	ASTM D4833	lbs	180	
Air Flow	ASTM D737	cfm	370	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D5261	oz/yd <sup>2</sup>	7.9
Thickness	ASTM D5199	mils	25
Fiber Content		100% Polypropylene	

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2013 TenCate Geosynthetics North America  
 Nicolon® is a registered trademark of Nicolon Corporation



FGS000113  
 ETQR11

