



# SHADE

## 44519

| Mechanical Properties   | Test Method | Unit | Typical Roll Value |    |
|-------------------------|-------------|------|--------------------|----|
|                         |             |      | MD                 | CD |
| Grab Tensile Strength   | ASTM D 4632 | lbs  | 120                | 85 |
| Trapezoid Tear Strength | ASTM D 4533 | lbs  | 70                 | 55 |
| Shade                   |             | %    | 52                 |    |
| Mullen Burst Strength   | ASTM D 3786 | lbs  | 260                |    |
| Puncture Strength       | ASTM D 4833 | lbs  | 35                 |    |

| Physical Properties | Test Method | Unit               | Typical Value |
|---------------------|-------------|--------------------|---------------|
| Weight              | ASTM D 5261 | oz/yd <sup>2</sup> | 2.5           |
| Fiber Content       |             |                    | 100% PP       |

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2012 TenCate Geosynthetics North America  
 Nicolon® is a registered trademark of Nicolon Corporation

