



## SCREEN FABRIC 45604

Mechanical Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D 4632	lbs	195	165
Trapezoid Tear Strength	ASTM D 4533	lbs	85	60
Open Area	COE-22125	%	40	
Mullen Burst Strength	ASTM D 3786	lbs	300	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D 5261	oz/yd <sup>2</sup>	3.7
Fiber Content			100% HDPE
Color			Amber

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2012 TenCate Geosynthetics North America  
Nicolon® is a registered trademark of Nicolon Corporation



FGS000097  
ETQR6

