



## WOVEN FILTRATION MEDIA

### 58600 WHITE – CC - HONEYCOMB FILTER

Mechanical Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D 4632	lbs	425	350
Trapezoid Tear Strength	ASTM D 4533	lbs	210	155
Puncture Strength	ASTM D 4833	lbs	165	
Burst	ASTM D 3786	psi	800	
Air Flow	ASTM D 737	cfm	1300	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D 5261	oz/yd <sup>2</sup>	10.1
Thickness	ASTM D 5199	mils	190
Fiber Content			100% PP
Construction		EPI x PPI	26 x 18

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2010 TenCate Geosynthetics North America  
 Nicolon® is a registered trademark of Nicolon Corporation



FGS000408  
 ETQR7

