



CONTAINMENT FABRIC

41589

Mechanical Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D 4632	lbs	250	250
Trapezoid Tear Strength	ASTM D 4533	lbs	115	115
Mullen Burst Strength	ASTM D 3786	psi	500	
Puncture Strength	ASTM D 4833	lbs	110	
UV Resistance (at 5000 hours)	ASTM G154	% strength retained	95	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D 5261	oz/yd ²	4.8
Construction		EPI/PPI	20 x 20
Fiber Content			100% PP

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.



FGS000179
ETQR2

