



10419 LENO/LOCK SHADE

Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Weight	ASTM D5261	oz/yd ²	1.9	
Grab Tensile Strength	ASTM D4632	lbs	80	85
Trapezoid Tear Strength	ASTM D4533	lbs	45	50
Mullen Burst Strength	ASTM D3786	psi	180	
Shade		%	40	

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2012 TenCate Geosynthetics North America
 Nicolon[®] is a registered trademark of Nicolon Corporation

