

20709 UV/FR TENNIS WINDSCREEN FABRIC

Mechanical Properties	Test Method	Unit	Typical Value	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs	270	200
Trapezoid Tear Strength	ASTM D4533	lbs	110	80
Air Flow	ASTM D737	cfm	400	
UV Resistance (at 1000 hours)	ASTM G154	%	71	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D5261	oz/sq yd	4.5
Fiber Content			100% PP

NOTE: This product meets or exceeds California State Fire Marshall Testing for flammability (Title 19, CCR Section 1237, CA State Fire Marshall Registration Number: F-40801 Registered Flame Resistant Product).

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Nicolon® is a registered trademark of Nicolon Corporation

Copyright © 2015 Nicolon Corporation. All Rights Reserved.

