



LATHE-LENO TENNIS WINDSCREEN

20813 Blue

Mechanical Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs	320	180
Trapezoid Tear Strength	ASTM D4533	lbs	120	75
Air Flow	ASTM D737	cfm	>300	
Shade		%	85	
UV Resistance at 3000 hours	ASTM G154	%	50	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D5261	oz/yd ²	4.9
Fiber Content		100% Polypropylene	

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2013 TenCate Geosynthetics North America
 Nicolon® is a registered trademark of Nicolon Corporation

