



25319 TRUCK COVER (w/o selvages)

Mechanical Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs	250	153
Trapezoid Tear Strength	ASTM D4533	lbs	125	65
Mullen Burst Strength	ASTM D3786	lbs	315	
Puncture Strength	ASTM D4833	lbs	80	
Air Flow	ASTM D737	cfm	>700	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D5261	oz/yd ²	6.0
Thickness	ASTM D5199	mils	40
Construction		EPI/PPI	15 x 7
Yarn Type		mils	Warp: 18 mil Fill: 25 mil
Fiber Content			PP Warp and PVC Fill

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2011 TenCate Geosynthetics North America
Nicolon® is a registered trademarks of Nicolon Corporation



FGS000045
ETQR11

