



3-Dimensional Woven Spacer Fabric 3D250W

Mechanical Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D 4632	lbs	675	325
Grab Tensile Elongation	ASTM D 4632	lbs	29	37
Compression Strength 10%	ASTM D 3575	%	25	
Compression Strength 20%	ASTM D 3575	%	27	
Compression Strength 50%	ASTM D 3575	%	32	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D 5261	oz/yd ²	19.7
Fiber Content			LDPE/PP

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2010 TenCate Geosynthetics North America
Nicolon® is a registered trademark of Nicolon Corporation

