



## GROUND COVER 47919

Mechanical Properties	Test Method	Unit	Typical Average Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D 4632	lbs	170	80
Grab Tensile Elongation	ASTM D 4632	%	22	15
Trapezoid Tear Strength	ASTM D 4533	lbs	70	50
Puncture	ASTM D 4833	lbs	75	
Water Flow	ASTM D 4491	gal/min/ft <sup>2</sup>	10	
UV Resistance @ 1200 hrs.	ASTM G 154 QUV	% strength retained	70	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D 5261	oz/yd <sup>2</sup>	3.2
Fiber Content			100% PP

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Nicolon® is a registered trademark of Nicolon Corporation.

Copyright © 2015 Nicolon Corporation. All Rights Reserved.

