



WOVEN FILTRATION MEDIA 58309 BLACK HUCKABACK E.A. FILTER

Mechanical Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D4632	lbs	250	145
Trapezoid Tear Strength	ASTM D4533	lbs	115	65
Air Flow	ASTM D737	cfm	> 1300	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D5261	oz/yd ²	4.1
Thickness	ASTM D5199	mils	35
Construction		EPI x PPI	33 x 20
Fiber Content			Polypropylene

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2012 TenCate Geosynthetics North America
Nicolon® is a registered trademark of Nicolon Corporation

