

PGM-G

Technical Data

TenCate Polyfelt® PGM-G paving composites are made of mechanically bonded 100 % PP continuous filament nonwoven reinforced by an alkali resistant glass filament grid.

TenCate Polyfelt® PGM-G grades were especially developed for new asphalt road construction, rehabilitation of older roads and conform to EN 15381. The main functions are Stress Relief (STR), Sealing (B) and Reinforcement (R). The products are used between asphalt layers, or applied directly on concrete surfaces or on cement stabilized layers.



TenCate Polyfelt® PGM-G

Properties	Standard	Unit	PGM-G 50/50		PGM-G 100/100		PGM-G 150/150		
Functions	EN 15381	-	STR + B + R		STR + B + R		STR + B + R		
Type of product	-	-	Asphalt Geocomposite, mechanically bonded continuous filament non woven with glass filament reinforcement						
Raw Material	-	-	100 % polypropylene, UV stabilized and alkali resistant glass filaments						
Tensile strength	MD/CD*	EN ISO 10319	kN/m	50 / 50	100 / 100	150 / 150			
Tensile strength at 2 %	MD/CD*	EN ISO 10319	kN/m	45 / 45	90 / 90	130 / 130			
Elongation at break		EN ISO 10319	%	3	3	3			
Bitumen retention**		EN 15381	kg/m ²	1.1	1.1	1.1			
** Bitumen required to saturate paving fabric only. This value does not indicate the bitumen application rate required for construction.									
E-Modulus (glass)			MPa	81 000	81 000	81 000			
Aperture size (indicative)			mm	22 x 22	18 x 18	24 x 11			
Total Mass per unit area	EN ISO 9864		g/m ²	350	550	750			
Melting point	EN ISO 3146		°C	Glass filaments are incombustible and temperature resistant up to 400 °C					
Forms of Supply									
Width			m	0.95	1.90	0.95	1.90	0.95	1.90
Length			m	100	100	100	100	70	70
Area			m ²	95	190	95	190	95	190
Roll weight			kg	37	73	60	110	55	105
Rolls per pallet			-	15	15	15	15	12	12
Roll diameter			m	0.40	0.40	0.42	0.42	0.40	0.40
Inner core diameter			m	0.12	0.12	0.12	0.12	0.12	0.12
Recycling				100 % recyclable with conventional methods					

* MD = Machine Direction / CD = Cross Direction

The values given are indicative and correspond to average values obtained in our laboratories and in independent testing institutes. The right is reserved to make changes without notice at any time.

The rolls must be kept in dry place! Installation Guidelines must be observed!

TENCATE GEOSYNTHETICS AUSTRIA GMBH

Schacher Mayerstr. 18 Tel. +43 732 6983 0, Fax +43 732 6983 5353
A-4021 Linz, Austria service.at@tencate.com, www.tencategeosynthetics.com

BeNeLux Tel. +31 546 544 811 service.nl@tencate.com
Central Eastern Europe Tel. +43 732 6983 0 service.at@tencate.com
Czech Republic Tel. +420 2 2425 1843 service.cz@tencate.com
France | Africa Fax +33 1 34 23 53 48 service.fr@tencate.com
Germany Tel. +49 30 3435 02 10 service.de@tencate.com
Italy Tel. +39 0362 34 58 11 service.it@tencate.com
Near Middle East Tel. +971 4810 3295 service.nme@tencate.com

Poland
Russia | CIS
Scandinavia | Baltics
Spain | Portugal
Turkey
UK | Ireland

Tel. +48 12 268 8375 service.pl@tencate.com
Tel. +43 732 6983 0 service.ru@tencate.com
Tel. +31 546 544 811 geonordic@tencate.com
Tel. +34 607 499 962 service.es@tencate.com
Tel. +43 732 6983 0 service.tr@tencate.com
Tel. +44 1952 588 066 service.uk@tencate.com



Quality - Environment - Safety

ISO 9001
ISO 14001
OHSAS 18001

www.dekra.seal.com

TenCate Geosynthetics Austria Gesm.b.H, TenCate Geosynthetics France S.A.S and TenCate Geosynthetics Netherlands b.v. are certified for the design, manufacturing and sales of geotextile and geotextile related products.