

TenCate Tecasafe® Plus - XL 9700 - XL 9240 - XL 9300.
 TenCate Tecasafe® - XA 1 - XA 9001 - XA 9002 - XA 9004 - XA 9030

GENERAL

- Sorting Sort the washing per colour and/or degree of soiling. When washing dyed and/or printed clothing, wash light and dark colours separately.
 Wash all flame inhibiting clothing separately from other clothing, in order to avoid the transfer of foreign flammable fibers or other materials.
- Detergent for colours For colours, use a detergent without optical whites, whenever possible.
- Dehydration Press with an adapted low pressure, or for a short period of time.
- Drying Drying in a finisher/tunnel gives a better appearance and less shrinkage than drying in a tumbler.
 Avoid excessive drying as this can damage the fabric.
- Accessories Hard materials (buttons/zips) can cause wear and tear.
- Stain removal Wash the clothing regularly to avoid fixation of stains.

HEAT- AND FLAME-RESISTANT PROPERTIES

- Rinsing heat- and flame-resistant material Rinse with soft water. Detergent residues can negatively influence the flame-retardant properties.
- Negative effect on flammability Do not allow the clothing to become excessively soiled, as this can have a negative effect on the flammability.
 It is better to increase the cleaning frequency.
- Post-wash treatment Softeners can negatively affect flame-retardant properties. A softener should only be applied to flame-retardant garments once its effect on the fire-resistant properties of the fabric has been tested.

HYDRO-TEC

- Detergent Use only laundry detergents suitable for Hydro-Tec.
 Remove all detergent residues, as they can have a negative effect on the fabric's water-repellent properties.
- Bleach Avoid using if possible.
- Wash temperature Maximum 60 °C. For the longest-lasting and optimum protection of Hydro-Tec finishes between washes, without reapplication, we recommend a max. temperature of 60 °C. Higher wash temperatures can negatively affect the Hydro-Tec finish.
- Drying As hot as possible – high drying temperatures reactivate the fluorine compounds and promote optimum repellence.
 Hydro-Tec is suitable for tumble and tunnel dryers. Avoid excessive drying as this can damage the fabric.
- Ironing Ironing has a positive effect on the reactivation of Hydro-Tec.
- Reapplication To get the best protection and maintain beading, Hydro-Tec must be reapplied after each wash. To ensure the optimum effect, please refer to the detergent and chemicals manufacturer. The application of impregnation agents to fabric to a domestic wash is not usually possible, so effective impregnation is only sensible in industrial laundries.

HYDRO-CONTROL™

TenCate has different washing instructions for Hydro-Control™ laminate fabrics.

Collection 2014. These recommendations have been compiled with the greatest care by TenCate Protective Fabrics EMEA. TenCate is not liable for damage caused by not (correctly) following this advice. No rights can be derived from these recommendations.