

TENCATE
Aralite® NP

FACE CLOTH: 100% NOMEX® fiber (spun)
BATT: 1 layer of needle punched non-woven; fiber composition Aramid
QUILT THREAD: Aramid
WEIGHT: 7.2 oz (sq yd)


ARALITE® NP lightweight thermal barrier fabrics provide a vital layer to insulate your body against intense heat. They feature less bulk and a wickable face cloth made with NOMEX® brand fiber for more comfortable and more flexible thermal protection. With proven protection and outstanding comfort, ARALITE NP is designed to meet your specific thermal, physical and budgetary requirements.

- Lightweight
- Balances insulative performance and heat stress relief
- Reduced bulk for improved comfort and flexibility
- Outstanding value
- Wickable face cloth for greater comfort

ARALITE NP delivers peace of mind when lives are on the line. Only by TenCate SouthernMills.

PHYSICAL PROPERTIES	ARALITE® NP	NFPA 1971-2007 Edition Requirements
Trapezoidal Tear Strength (lbs) Initial (warp x fill) After 5 launderings (warp x fill)	ASTM D5587* 55 x 35 50 x 40	5.0 min
Thermal Protective Performance (cal/cm²) TPP with ADVANCE™, Crosstech® Type 2c	NFPA 1971-2007 42 - 44	35.0 min
Vertical Flammability Char Length in inches (warp x fill) (Initial) Char Length in inches (warp x fill) (After 5 launderings) After Flame in seconds (warp x fill)	ASTM D6413 <1.5 <1.0 <0.5	4.0 max 2.0 max
Laundry Shrinkage (%) After 5 launderings (cotton sturdy cycle) (warp x fill)	AATCC 135 < 5.0 x < 5.0	5.0 max
Thermal Shrinkage (%) 500°F at 5 minutes After 5 launderings	NFPA 1971-2007 < 2.0 < 1.5	10.0 max
Heat Resistance	NFPA 1971-2007 Pass	Shall not melt, separate or ignite

*NFPA 1971-2007 stipulates that Trapezoidal Tear Strength measurement shall be performed without specimen slippage.



The Most Trusted Name In Protective Fabrics.

SOUTHERN MILLS, Inc.
6501 Mall Blvd.
P.O. Box 289
Union City, GA 30291
Phone: 770.969.1000
Fax: 770.969.6846
800.241.8630

www.southernmills.com

To the best of our knowledge, the information contained herein is accurate. However, SOUTHERN MILLS assumes no liability whatsoever for the accuracy or completeness of the information contained herein. Users of any substance must satisfy themselves by independent investigation that the material can be used safely. We have described certain hazards, but we cannot guarantee that these are the only hazards.

©2007 SOUTHERN MILLS, Inc. TENCATE is a trademark of ROYAL TEN CATE NV. SOUTHERNMILLS and ADVANCE are trademarks of SOUTHERN MILLS, Inc. ARALITE is a registered trademark of SOUTHERN MILLS, Inc. Crosstech is a registered trademark of W.L. Gore & Associates. DuPont™ and NOMEX® are trademarks or registered trademarks of DuPont or its affiliates. SOUTHERN MILLS, Inc. patents pending.

