### TECASAFE®PLUS



### **Tecasafe®Plus Swiss Pique**

#### **PROFESSIONAL LOOK**

A Swiss Pique knit construction delivers increased ease-of-motion while serving as a clean alternative to woven button up shirts.

## COOL, DRY, AND COMFORTABLE

Integrated wicking Coolderm™ technology offers enhanced moisture management to promote body temperature regulation and breathability.

#### **COLOR AND CONFIDENCE**

Tecasafe® Plus stands up to repeated laundering and resists fading in both light shades and Truecolor® technology-powered dark shades.



# TECASAFE®PLUS

TECHNICAL DATA*	TECASAFE®PLUS SP	TECASAFE®PLUS SP TRUECOLOR®
Nominal Weight	6.7 osy (227 gsm)	6.7 osy (227 gsm)
Construction	Knit	Knit
Color	Orange, Hi-Vis Yellow, Khaki, Light Blue	Navy, Heather Gray, Gray, Black
Fiber Content	Modacrylic, Lyocell, Aramid	Modacrylic, Lyocell, Aramid
Certification(s)	ASTM 1506, NFPA 1975, NFPA 2112	ASTM 1506, NFPA 1975, NFPA 2112

Thermal Testing (Flame Resistance)				
Manikin Burn NFPA 2112	Predicted Body Burn		Pass	Pass
Energy Breakopen Threshold NFPA 70E, ASTM 1959	ATPV Rating		8.3 cal/cm <sup>2</sup>	8.2 cal/cm²
	PPE Category		Category 2	Category 2
Vertical Flame	Initial and 100x after	After flame	< 2.0 sec	< 2.0 sec
ASTM 6413, NFPA 2112	wash	Char length	< 4.0 in (100 mm)	< 4.0 in (100 mm)
Thermal Shrinkage NFPA 2112	Initial and 3x after wash		< 10 %	< 10 %

Physical Testing				
Burst Strength – Ball Method ASTM D3787  Burst Strength – Mullen Method ASTM D3786		99 lbf (440 N)	105 lbf (460 N)	
		100 psi (675 kPa)	100 psi (675 kPa)	
Dimensional Stability AATCC 135		< 5.0 %	< 5.0 %	
Fabric Stretch and Recovery	Fabric Stretch	16% x 42%	32 % x 20 %	
warp x fill	Fabric Recovery	95% x 91%	90 % x 94 %	

Comfort				
Air Permeability ASTM D737	ermeability <sup>D737</sup>		280 ft³/min/ft²	170 ft³/min/ft²
Appearance *Score 5 (best) to 1 (Worst)				
	Laundering AATCC 61 2A	Shade Change	Up to 4 *	Up to 4 - 5 *
	Yenon Light			

	Laundering AATCC 61 2A	Shade Change	Up to 4 *	Up to 4 - 5 *
Color Fastness	Xenon Light Exposure AATCC 16	After 40 hours	Up to 4 - 5 *	Up to 4 - 5 *
	Pilling Resistance ASTM D3512	Initial: 60 min	Up to 4.5 *	Up to 4 *

 $<sup>^{*}</sup>$  All values subject to final certification and specification. Tested on specific colors. Appearance is dependent on shade of fabric.

AVAILABLE C	OLORS	OPTIONAL COLORS		
Orange	Hi-Vis Yellow	Khaki	Light Blue	Additional color options may be available. Please contact TenCate Protective Fabrics for more information.
Navy	Heather Gray	Gray	Black	Color shades and textures may vary. Please contact your sales representative for swatch samples.









All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.